

INSITUFORM® MATERIALKENNWERTE (LANGZEITWERTE)

	LONDON-HACKNEY					HAMBURG: HOLZMÜHLENSTRASSE	
Vorgabe / Betriebsdauer: Einheit	WIS 4-34-04 Standard* N/mm ²	1991 20 Jahre* N/mm ²	1997 25 Jahre* N/mm ²	2001 30 Jahre* N/mm ²	1983 Ins Vorgabe N/mm ²	25 Jahre* N/mm ²	
Biegefestigkeit Muster 1	25	46	43	39	34	47,8	
				43		38,2	
				47		34,4	
Biege-E-Modul Muster 1	2.200	2.900	2.930	3.100	2.200	3.120	
				3.500		2.378	
				3.300		2.300	
Wanddicke Muster 1	9	6,3	5,22	5	7,5	6,46	
						6,18	
						6,32	

*WIS 4-34-04 April 1986: Issue 1,

*MTS Pendar

*IB Rolf Siebert

*Bodycote

*IB Siebert + Krippschild (2007)

"Specification for Polyester

Insituform Sewer Linings"